



MaxxBreak OS-936
Organo-Silicone Emulsion Antifoam

MaxxBreak OS-936 is an organo-silicone defoamer for evaporator columns, paints, adhesives and a wide variety of defoaming applications. **MaxxBreak OS-936** is extremely effective at low concentrations. **MaxxBreak OS-936** can be added as received or pre-diluted with water or one of the formula ingredients. Normally the low end of 0.05-0.1% will effectively prevent air entrapment in most systems. In paint manufacturing it is usually advantageous to divide the defoamer addition into two parts. One part is added to the pigment prior to grinding and the second part is added to the let down portion of the paint. **MaxxBreak OS-936** is a highly effective long lasting antifoaming agent. If frozen it should be warmed to room temperature and mixed prior to use. In paint and coatings testing for leveling and fisheyes best results are normally achieved 24 hours after compounding. In certain cases best results are obtained by adding all of the defoamer in paint formulations prior to grinding to insure proper dispersion throughout the system.

TYPICAL PROPERTIES

Appearance	Hazy Straw Liquid
Ionic Nature	Nonionic
pH, 2% Solution	7.0
Water Solubility	Excellent
Active Ingredients	100%
Flash Point, °F	270
Pour Point, °F	-60

PERFORMANCE FEATURES

Effective at low concentrations, Excellent Water Stability

SUGGESTED USES

Paints, Adhesives, Detergents, Inks, Graphic Arts, Evaporator Columns

Let MCTRON Technologies raise your expectations.

McTron Technologies, LLC Technical Support Team is available to provide assistance with the formulation of all our products to optimally suit your specific needs.

McTron Technologies LLC Guarantee

If any product is defective in workmanship or materials, McTron Technologies, LLC will replace the product, or refund the full purchase price. This warranty is in place of all other warrants, expressed or implied, and all implied warrants of a product for an intended use shall be solely up to the user. McTron Technologies, LLC assumes no liability for consequential damages. Its liability shall in no event exceed the purchase price of materials supplied by it.