MaxxBreak OB-396 NS
Oil-Based Defoamer

MCTRON TECHNOLOGIES

PRODUCT DESCRIPTION

MaxxBreak OB-396 NS is a defoamer for latex paints and coating systems but is also extremely universal in defoaming applications.

Benefits & Features

▸ **Highly effective**

▸ **Versatile, Long lasting**

▸ **Efficient antifoaming**

▸ **Freeze/Thaw Stable**

▸ **"Fish-eye" leveling**

▸ *Stir before use*

TYPICAL PROPERTIES

Appearance	Hazy Straw Liquid
Weight/Gallon	7.6 lbs.
Ionic Nature	Nonionic
Solubility	Dispersible
Actives	100%
Viscosity, cps@25C	Medium Viscosity Fluid
Percent Active	100
pH, *1% solutions*	6.6
Flash Point	>300F

APPLICATION & DOSAGES

0.05 – 0.1% of **MaxxBreak OB-396 NS** dosage is the recommended starting point. It is usually advantageous to divide the defoamer addition into two parts. One part added to the pigment prior to grinding and the second part added to the let down portion of the paint or coating. For best leveling of "fish-eye free" coatings, the defoamer system should be evaluated not less that 24 hours after the defoamer has been added.

HANDLING & STORAGE

The manufacture of this product is within the scope of the ISO 9001 Quality Management System. **MaxxBreak® OB-396 NS** is stable in freeze conditions but requires mixing after thawing. Please see the Material Safety Data Sheet before handling this product.

Let MCTRON Raise Your Expectations...

MCTRON's Technical Support Team is available to assist with the formulation of all our products to optimally suit your specific production needs and manufacturing environment.

MCTRON Technologies Guarantee

If any product is defective in workmanship or materials, MCTRON Technologies, LLC will replace the product, or refund the full purchase price. This warranty is in place of all other warrants, expressed or implied, and all implied warrants of a product for an intended use shall be solely up to the user. MCTRON Technologies, LLC assumes no liability for consequential damages. Its liability shall in no event exceed the purchase price of materials supplied by it.