



Maxxacryl® AC- 3164 Acrylic Emulsion Polymer

MaxxAcryl AC-3164 is a tacky elastomeric acrylic polymer. Coatings formulated with this product has good adhesion to both polar and non-polar substrates. **MaxxAcryl AC 3164** has excellent low temperature flexibility, and it can be used to add flexibility to harder polymers. It is tacky at room temperature, which allows it to be used in dust collection applications.

TYPICAL PROPERTIES

Type	Acrylic Emulsion Polymer
Total Solids	56%
Weight per Gallon	8.46
T _g	-42°C
MFFT (<i>ASTM D-235</i>)	<0°C
Particle Size	0.25 microns
pH	6.5
Viscosity (<i>Brookfield RVT #3/100rpm</i>)	100-1000 cps
Surfactant Charge	Anionic
Bulking Value	0.1182 gal./lb.
Freeze Thaw Stability	Do Not Freeze

Performance Features

Excellent Tack – Maintains Tack with Aging – Excellent Compound Base

Suggested Use

Dust Collection – Pressure Sensitive’s - Mastics

Let MCTRON Technologies raise your expectations.

McTron Technologies, LLC Technical Support Team is available to provide assistance with the formulation of all our products to optimally suit your specific needs.

McTron Technologies LLC Guarantee

If any product is defective in workmanship or materials, McTron Technologies, LLC will replace the product, or refund the full purchase price. This warranty is in place of all other warrants, expressed or implied, and all implied warrants of a product for an intended use shall be solely up to the user. McTron Technologies, LLC assumes no liability for consequential damages. Its liability shall in no event exceed the purchase price of materials supplied by it.