

Maxxacryl® SA-202 Styrene Acrylic Emulsion Polymer



PRODUCT DESCRIPTION

Maxxacryl SA-202 very soft self crosslinking styrene-acrylic emulsion with good water and solvent resistance. It is made with a co-polymerizable surfactant to eliminate re-wetting and can be formulated with a high level of filler.

TYPICAL PROPERTIES

Appearance	White liquid
Solids,%	50
pH	4.0
Viscosity, cps	200
Tg (°C)	-20

HANDLING & STORAGE

Store at an even temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 12 months following delivery. Product should be used as soon as possible after opening. Consult the SDS for more details.

Let MCTRON Raise Your Expectations...

MCTRON's Technical Support Team is available to assist with the formulation of all our products to optimally suit your specific production needs and manufacturing environment.

MCTRON Technologies Guarantee

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. McTron Technologies shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond McTron Technologies direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. Product safety information required for safe use is not included. **BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR MCTRON TECHNOLOGIES REPRESENTATIVE OR DISTRIBUTOR.**

Benefits & Features

- ▶ **Soft, strong film**
- ▶ **Water resistance**
- ▶ **Easy to compound**
- ▶ **Compatibility wide wide range of pigments and fillers**

APPLICATION & DOSAGES

Maxxacryl SA-202 can be used as a binder for water-resistant coatings for use in textile back coating and textile finishing applications.